

THERMOPLASTIC RESIN COMPOSITION, PRODUCTION THEREOF, AND GAS-BARRIER FILM THEREFROM

Patent Number: JP8053572
Publication date: 1996-02-27
Inventor(s): KAWAI MICHIO; others: 01
Applicant(s): MITSUBISHI CHEM CORP
Requested Patent: ☐ JP8053572
Application Number: JP19940189384 19940811
Priority Number(s):
IPC Classification: C08K7/00; C08K3/32; C08K3/34; C08L101/00
EC Classification:
Equivalents:

Abstract

PURPOSE:To obtain a thermoplastic resin composition in which a laminar silicate salt or a laminar phosphate salt is dispersed in a thermoplastic resin in a finely cleaved state, thus is useful as a film or the like because it is excellent in balance in mechanical properties, resistance to heat distortion and gas barrier properties.

CONSTITUTION:This composition comprises (A) a thermoplastic resin, for example, polypropylene resin or polyamide resin and (B) a laminar compound selected from a laminar silicate salt and a laminar phosphate compound having a substantially inactive compound (preferably an organic onium ion having 12 C or more alkyl group) between layers wherein the amount of component B is 0.01-40wt.% calculated as ash and more than 40wt.% of component B is dispersed in component A in 0.05-10nm thickness. This composition is obtained in a powdery composite form by loading stress and compression force of higher than 500sec<-1> shear rate to a powdery mixture of components A and B simultaneously at a temperature lower than the softening point of component A.

Data supplied from the esp@cenet database - I2